

Espuma de PVC 60



Densidad kg/m ³	ASTM D1622	kg/m ³	nominal	60
Resistencia a la compresión	ASTM D1621-10	MPa	average min-ave min-min	0,96 0,75 0,61
Modulo de compresión	ASTM D1621-10	MPa	average min-ave min-min	46 31 25
Resistencia a la rotura	ASTM D1623	MPa	average min-ave min-min	2,11 1,33 1,19
Modulo de rotura	ASTM D1623	MPa	average min-ave min-min	106 75 66
Resistencia al corte	ASTM C273	MPa	average min-ave min-min	0,77 0,70 0,60
Modulo de corte	ASTM C273	MPa	average min-ave min-min	21 17 14
Alargamiento de corte a la rotura	ASTM C273	%	average	13
Medidas estandar		mm		1150 2450 78